

EZYCOAT FINE FINISH**DESCRIPTION AND COMPOSITION**

Ezycoat Fine Finish is essentially an acrylic texture finish consisting of a fine grade of quartz fillers and binders of the highest quality integrated with in a mixture of acrylic emulsion and pigments to produce the ultimate in pigmented texture finishes.

This product has been specifically designed as a top coat to various cementitious render and skim rendered surfaces. Its silky smooth finish also makes it attractive for use over a variety of fibre cement cladding systems and pre-cast concrete.

Ezycoat Fine Finish is a one part product that once mixed is ready for immediate use straight from the pail. The fine quartz fillers allow Ezycoat Fine Finish to be troweled out to a thickness of 1mm. Thus allowing ease of use and producing a scrub Fine finish second to none. It exhibits excellent adhesion and flexibility.

USE

Ezycoat Fine Finish has been designed to produce a highly decorative external synthetic finish which is suitable for application to a variety of surfaces as a top coat or as a leveling coat and finish. Ezycoat Fine Finish is suitable for use in conjunction with Ezycoat Polymer, in particular when coating manufacture specification installed Fibre cement sheeted surfaces. Its ability to adhere to smooth surfaces

and flexible nature make it suitable for many types of application. It also suitable for use as a finish over existing traditional rendered or EzySkim Render/ Ezycoat Super 6 surfaces.

When applying Ezycoat Fine Finish to any surface it is recommended that the surfaces be free of any contaminant which may affect the performance of the coatings and that any visible imperfections in the surface which may be transferred through to the finished surface be patched using Ezycoat Coarse or Smooth Patch. (see Ezycoat Coarse Patch and Smooth Patch Technical Data sheets)

APPLICATION

Once having produced a uniform substrate by either cement rendering, **EzySkim Render/ Ezycoat Super 6** or **Ezycoat Patching**, apply a base coat of **Ezycoat HiOpacity Sealer** (see Ezycoat HiOpacity Sealer Technical Data Sheet) maintaining even coverage. Then allow the treated surface to stand for approximately 1 hour, prior to applying **Ezycoat Fine Finish**. Then using a stainless steel plasterer's trowel, evenly spread the paste over the surface.

Depending on the surface to be coated, it may be necessary to apply the **Ezycoat Fine Finish** in 2 coats. The first being the leveling coat which will be left as a float finish and the second the finishing coat. The finishing coat may be finished

EZYCOAT FINE FINISH

flat with a plastic trowel and then lightly sponged off to provide a sandy finish to the surface.

Ezycoat Membrane Paint is then applied in accordance with the **Ezycoat Membrane** specifications, approximately 12 hrs after the application of the **Ezycoat Fine Finish**. This will complete the application process, producing a durable and aesthetically pleasing finish.

Consumption: 2 Coat - 8 sqm per 15 Lit.

1 Coat - 15 sqm per 15 Lit.

Pail Size: 15Lit.

Classification: Non-dangerous goods

Colours: White

EZYCOAT SPECIFICATION SEQUENCE

(See relevant Technical Data Sheets for products listed)

*For Pre **EzySkim Rendered** or **Ezycoat Super 6** Surfaces(See Technical Data Sheet for the Ezycoat Product mentioned before proceeding) or specification installed Fibre cement sheeting systems suitably designed to accept a texture system.

(See Technical Data Sheet 10045 for surface preparation methods for Fibre cement sheeting prior to proceeding with this sequence).

Coating Sequence	Product	Use
1.	Ezycoat Hi Opacity Sealer	Sealer Roll-on/ Brush
2.	Ezycoat Fine Finish For 2 Coats Repeat step2	Stainless Steel Trowel then float & finish with Plastic and/or Sponge Float
3.	Ezycoat Membrane	Brush/ Roll-on Paint 2 Coat application

*Prior to the application sequence the surfaces should be cleaned and free of any contaminant, releasing agent, fungal growth which may affect the performance of these coatings. Any imperfections which may become visible in the finished surface should be patched and leveled with Ezycoat Patching compounds. Any structural imperfections and/or cracks will need to be stabilised prior to any further application.

Note:

Ezycoat Fine Finish should not be applied at temperatures below 7 degrees Celsius or when there is the possibility of rain. The durability of the product in its original confection is guaranteed for 1 year as long as it is not exposed to direct sunlight or temperatures below 4 degrees. **Ezycoat Fine Finish** is not suitable for use in areas prone to water logging, submersion, continually damp and/or below ground. Walls where **Ezycoat Fine Finish** is to be applied must be free draining. In the case of retaining walls the rear of the wall must be engineered to prevent any penetration of moisture or water through the wall in to the rear

EZYCOAT FINE FINISH

of the **Ezycoat Fine Finish**. Failure to do so will result in damage to the **Ezycoat Fine Finish** and is not covered by warranty.

EXCESS WASTE

Excess Waste product should be disposed of in a responsible manner following guidelines as set out by the local council's by-laws and Waste Disposal Procedures.

For more detailed information with regards this product and safety issues, please refer to the Material Safety Data Sheets available from Active Building Systems Pty Ltd upon request.

Ezycoat Fine Finish is to be applied by suitably licensed persons holding a license for this trade as recognised by the legislative building authority for the relevant state to which the work is being carried out. Misuse of this product and/or non compliance with technical specifications will void any warranties whether verbal or written. Active Building Systems Pty Ltd reserves the right to change, update and republish these specifications without any notice. It is the user's responsibility to attain the most current publication of Ezycoat Specifications from Active Building Systems Pty Ltd.