

EZYCOAT SANDSTONE**DESCRIPTION AND COMPOSITION**

Ezycoat Sandstone is an acrylic texture finish. It consists of a coarse grade of quartz fillers and marble mixed with binders integrated with in a mixture of acrylic emulsion and pigments. This decorative granular finish emulates what 'mother nature' has taken a lifetime to produce, with the assistance of extreme temperature and pressure creating a fusion of various mineral particles. **Ezycoat Sandstone** replicates this product giving you versatility in extending the decorative finish parameters. **Ezycoat Sandstone** joins the range of decorative finishes such as **Ezycoat Fine Finish & Ezycoat Polymer** to provide a product that has been specifically designed as a top coat to various cementitious render and skim rendered surfaces. Its coarse granular appearance makes it attractive for use over a variety of fibre cement cladding systems and precast concrete surfaces. **Ezycoat Sandstone** is a one part product that once mixed is ready for immediate use straight from the pail. The coarse granular particles allow **Ezycoat Sandstone** to be troweled on in a one coat application, with the ability to cater for minor imperfections which may exist in the surface.

USE

Ezycoat Sandstone has been designed to produce a highly decorative external synthetic finish which is suitable for application to a variety of surfaces as a top coat. **Ezycoat Sandstone**

is suitable for use in conjunction with **Ezycoat Polymer**. Its granular consistency makes it ideal for surfaces that require high build coatings, in particular for manufacture specification installed Fibre cement sheeted surfaces. Its ability to adhere to smooth surfaces and flexible nature make it suitable for many types of application. It also suitable for use as a finish over existing traditional rendered or **EzySkim Render/ Ezycoat Super 6** surfaces.

When applying **Ezycoat Sandstone** to any surface it is recommended that the surfaces be free of any contaminant, which may affect the performance of the coatings and that any visible imperfections in the surface which may be transferred through to the finished surface be patched using **Ezycoat Coarse or Smooth Patch**. (see Ezycoat Coarse Patch and Smooth Patch Technical Data sheets)

APPLICATION

Once having produced a uniform flat substrate, apply a base coat of **Ezycoat HiOpacity Sealer** (see Ezycoat HiOpacity Sealer Technical Data Sheet) maintaining even coverage. Then allow the treated surface to stand for approximately 1 hour, prior to applying **Ezycoat Sandstone**. Using a stainless steel plasterer's trowel, evenly spreading the paste over the surface.

Due to the high build nature of **Ezycoat Sandstone** in most cases it will only be

EZYCOAT SANDSTONE

necessary to apply the finish in one coat, however should the need arise for a 2 coat process then the first coat should be applied using either **Ezycoat Polymer** or **Ezycoat Sandstone**. The first being the leveling coat which will be left as a float finish and the second the finishing coat. The finishing coat is to be finished flat with a plastic trowel.

Ezycoat Membrane Paint is then applied in accordance with the **Ezycoat Membrane** specifications, approximately 12 hrs after the application of the **Ezycoat Sandstone**. This will complete the application process, producing a durable and aesthetically pleasing finish.

Consumption: 6 - 8 sqm per 15 Lit.

Pail Size: 15Lit.

Classification: non-dangerous goods

Colours: White Base Tinted on Request

EZYCOAT SPECIFICATION SEQUENCE

(See relevant Technical Data Sheets for products listed)

*For Pre **EzySkim Rendered** or **Ezycoat Super 6** Surfaces(See Technical Data Sheet for the Ezycoat Product mentioned before proceeding) or specification installed Fibre cement sheeting systems suitably designed to accept a texture system. (See Technical Data Sheet 10045 for

surface preparation methods for Fibre cement sheeting prior to proceeding with this sequence).

Coating Sequence	Product	Use
1.	Ezycoat Hi Opacity Sealer	Sealer Roll-on/ Brush
2.	Ezycoat Sandstone	Stainless Steel Trowel then float & finish with Plastic Float
3.	Ezycoat Membrane	Brush/ Roll-on Paint 2 Coat application

*Prior to the application sequence the surfaces should be cleaned and free of any contaminant, releasing agent, fungal growth which may affect the performance of these coatings. Any imperfections which may become visible in the finished surface should be patched and leveled with Ezycoat Patching compounds. Any structural imperfections and/or cracks will need to be stabilised prior to any further applications.

Note:

Ezycoat Sandstone should not be applied at temperatures below 7°C or when there is the possibility of rain. The durability of the product in its original confection is guaranteed for 1 year as long as it is not exposed to direct sunlight or temperatures below 4 degrees.

Ezycoat Sandstone is not suitable for use in areas prone to water logging, submersion, continually damp and/or below ground. Walls where **Ezycoat Sandstone** is to be applied must

be free draining. In the case of retaining walls the rear of the wall must be engineered to prevent any penetration of moisture or water through the wall in to the rear of the **Ezycoat Sandstone**. Failure to do so will result in damage to the **Ezycoat Sandstone** and is not covered by warranty.

EXCESS WASTE

Excess Waste product should be disposed of in responsible manner following guidelines as set out by the local council's bi-laws and Waste Disposal Procedures.

For more detailed information with regards this product and safety issues, please refer to the Material Safety Data Sheets available from Active Building Systems Pty Ltd upon request.

Ezycoat Sandstone is to be applied by suitably licensed persons holding a license for this trade as recognised by the legislative building authority for the relevant state to which the work is being carried out. Misuse of this product and/or non compliance with technical specifications will void any warranties whether verbal or written. Active Building Systems Pty Ltd reserves the right to change, update and republish these specifications without any notice. It is the user's responsibility to attain the most current publication of **Ezycoat** Specifications from Active Building Systems Pty Ltd.