

Certificate of Analysis

Clearsafe Environmental Solutions Pty Ltd

16 Stewart St, Wollongong NSW 2500

info@clearsafe.com.au

1300 042 962

Report Number: 20-1040-266-ID

Date of Report: 29/2/2016

Date of Analysis: 29/2/2016

Site Address: Asbestos Analysis - Various

Refer to Notes

Client Name: Non-Account Customer

Client Address:

Client Contact: Firecrunch Australia
(PETER@FIRECRUNCH.COM.AU)

Sampled By: As Received

Approved Identifier: Luke Heckenberg

Approved Signatory: Luke Heckenberg

Test Method: Asbestos identification in bulk samples by polarised light microscopy and dispersion staining, in accordance with 'AS4964-2004 Method for the Qualitative Identification of Asbestos in Bulk Samples' and Clearsafe Method SOP.ID.01 [Detection Limit - 0.1g/kg (AS4964)].

Notes: The results contained within this report relate only to the samples tested. This report should not be copied, presented or reviewed except in full.

An independant analytical technique is recommended for confirmation of vinyl and bituminous samples, or samples in which 'Unknown Mineral Fibre' is detected.

NATA accreditation relates to the analysis of the sample(s) and does not cover the sample collection process.

Sample Number	Sample Reference / Location	Description **	Result *
20-1040/351	Firecrunch MBE 10	FCS, White, Glassy Rod-Like Fibres, Ribbon-Like Fibres. Sample Size: 150x100x10mm	No Asbestos Detected ^{6, 5}
20-1040/352	Firecrunch MBE 20	FCS, Grey, Glassy Rod-Like Fibres, Ribbon-Like Fibres. Sample Size: 120x65x20mm	No Asbestos Detected ^{6, 5}

*** Result Codes:**

- | | |
|-----------------------------------|---|
| 1 - Chrysotile Asbestos Detected | 4 - Unknown Mineral Fibre Detected |
| 2 - Amosite Asbestos Detected | 5 - Synthetic Mineral Fibre (SMF) Present |
| 3 - Crocidolite Asbestos Detected | 6 - Organic Fibres Present |

**** Description Codes:**

FCS - Fibrous Cement Sheeting VFT - Vinyl Floor Tile

20-1040-266-ID



NATA Accredited Laboratory No. 18542

Accredited for compliance with ISO/IEC 17025. The results of the tests, calibrations and/or measurements included in this document are traceable to Australian / national standards.